



To

UNION FOAM S.p.A.

Via dell'Industria, 11

20040 BELLUSCO (MI)

Date, 31st March, 2004
RP n° 172/A
Ref. Fax dated 27.02.04

Received 11.03.04

Start tests 11.03.04

End tests 29.03.04

Page 1 of 1

T E S T R E P O R T

Subject: DETERMINATION OF THE OZONE RESISTANCE OF THE REPRESENTATIVE SAMPLE OF EUROBATEX WHEN SUPPLIED IN THE FORM OF FLEXIBLE CELLULAR TUBE OR SHEET

SAMPLE

EUROBATEX

Test Method

Ozone resistance
50 pphm - 40°C - 72 hours

No cracks visible at 7 X

ISO 7326/91
Method 1 (tube)
Method 2 (sheet)
ASTM D 1171/94

The contained results refer only to the tested sample.

This report cannot be partially reproduced without the laboratory approval.

L. Lamboglia, Operator



F. Casa, Director